

## WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



### INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: C04B 18/10, F23G 5/40, 7/10

(11) International Publication Number:

WO 95/10488

(43) International Publication Date:

20 April 1995 (20.04.95)

(21) International Application Number:

PCT/GB94/02106

A1

(22) International Filing Date:

28 September 1994 (28.09.94)

(30) Priority Data:

93/21359.3

15 October 1993 (15.10.93)

GB

(71) Applicant (for all designated States except US): KINGSWAY GROUP PLC [GB/GB]; Celcon House, 289-293 High Holborn, London WC1V 7HJ (GB).

(72) Inventors; and

- (75) Inventors/Applicants (for US only): COOK, Colin, Brian [GB/GB]; 56 Lonfield Avenue, High Halstow, Rochester, Kent ME3 8TA (GB). SPEARE, Philip, Reginald, Stuart [GB/GB]; 55 Cambridge Road, London SW20 0PX (GB). TEBBIT, John, Beresford [GB/GB]; 1 West View, Maidstone Road, Headcorn, Kent ME14 9RL (GB).
- (74) Agent: PRENTICE, Raymond, Roy; R.R. Prentice & Co., The Hop Exchange, 24 Southwark Street, London SE1 1TY (GB).


(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CL, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ).

**Published** 

With international search report.

### BEST AVAILABLE COPY

(54) Title: IMPROVEMENTS IN THE PRODUCTION OF BIOGENETIC SILICA FROM ORGANIC PLANT MATTER



#### (57) Abstract

In a method for the production of biogenetic silica from organic plant matter, the plant matter is fed continuously by a screw conveyor (13) from a hopper (12) to a furnace in the form of an inclined tube (11) which is maintained at a temperature of about 450° and rotated at a speed of about 1 rpm. The material travels down the inclined tube and is retained in the furnace for no more than about 30 minutes. Biogenetic silica is collected from the lower end of the tube (11) in a collection can (18) and is allowed to cool. The inclined tube (11) may be mounted on a wheeled platform (19) so that the furnace is portable.

### FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

		GB	United Kingdom	MR	Mauritania
ΑT	Austria	GE	Georgia	MW	Malawi
ΑÜ	Australia	_	Guinea	NE	Niger
BB	Barbados	GN		NL	Netherlands
BE	Belgium	GR	Greece	NO	Norway
BF	Burkina Faso	HU	Hungary	NZ.	New Zealand ·
BG	Bulgaria	ie.	Ireland	PL	Poland
BJ	Benin	TT.	Italy	PT	Portugal
BR	Brazil	JP	Japan		Romania
BY	Belarus	KÆ	Kenya	RO	Russian Federation
CA	Canada	KG	Kyrgystan	RU	-
CF	Central African Republic	KP	Democratic People's Republic	SD	Sudan
CG	Congo		of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CI		LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	TD	Chad
CN	China	LU	Luxembourg	TG	Togo
CS	Czechoslovakia	LV	Latvia	TJ	Tajikistan
CZ	Czech Republic	MC	Monaco	TT	Trinidad and Tobago
DΕ	Germany	MD	Republic of Moldova	UA	Ukraine
DK	Denmark	MG	Madagascar	US	United States of America
ES	Spain		-	UZ	Uzbekistan
FI	Finland	ML	Mali	VN	Viet Nam
FR	Prance	MN	Mongolia	,.,	
GA	Gabon				

- 1 -

# Title: IMPROVEMENTS IN THE PRODUCTION OF BIOGENETIC SILICA FROM ORGANIC PLANT MATTER

This invention relates to improvements in the production of biogenetic silica from organic plant matter and is particularly concerned with the production of ash from rice hulls or husks, rice stalks, equisetum (commonly known as horsetails), palm leaves and in particular those of the palmyra palm as well as sunflowers and bamboo.

)

)

10 The disposal of rice husks is a substantial problem for rice growers since the husks are not suitable for use as fertilisers and up until now have had to be disposed of either by burying or burning. Space for burying is frequently not available in heavily populated areas and burning creates undesirable atmospheric pollution. However, as is known, rice husks contain a high amount of biogenetic silica and it is possible to produce pozzolanic material from rice husk ash which has great potential economic advantages for developing countries that have large quantities of rice husks readily available and virtually free of cost.

Attempts have previously been made to utilise rice husks mixed with Portland cement to make blocks. It has generally been possible to meet strength requirements but the cup-like form of the husks requires an excessive amount of cement and thus such blocks are not economic. Accordingly, it has been proposed to reduce the rice husks to ash form for use in the production of pozzolanic material.

- 2 -

In the conversion of rice husks to ash, the combustion process removes the organic matter and leaves a silica rich residue. When rice husks are first heated, weight loss occurs up to 100°C by evaporation of absorbed water. At about 350°C, the volatiles ignite causing further weight loss and the husks begin to burn. From 400°C to 500°C, the residual carbon oxidises and the majority of weight loss occurs in this period. The silica in the ash is still in amorphous form. Above

)

)

In previous work carried out on rice husk ash, the ash was produced by burning large quantities of rice husks in a heap in a furnace, often for long periods. Under these conditions, the optimum burning regime had been found to be a temperature of 450°C for 3 hours. The energy requirement under these conditions makes production uneconomic for most, if not all, commercial applications. Similar problems are encountered with the combustion of other organic plant matter of the kind referred to above.

The present invention therefore seeks to improve the production of rice husk ash to enable it to be produced economically on a commercial basis and the primary aim of the invention is to provide an improved method of producing biogenetic silica from organic plant matter.

According to the invention there is provided a method for the production of biogenetic silica from organic plant matter in which the plant matter is fed continuously to an inclined rotating furnace maintained at a temperature of between 400 and 500°C, the material

PCT/GB94/02106 WO 95/10488

- 3 -

is retained in the furnace for no more than about 30 minutes and biogenetic silica is continuously collected from the furnace and allowed to cool.

preferably, the rotating furnace is maintained at a temperature of about 450°C and the material is desirably retained in the furnace for between 15 and 30 minutes.

The organic plant matter is desirably fed into the upper end of the inclined rotary furnace via a hopper. The biogenetic silica, which normally takes the form of ash, may be collected from the lower end of the furnace via a chute.

)

)

The organic plant matter may be ground to a powder before being fed to the furnace.

According to a preferred embodiment of the invention, the organic plant matter takes the form of rice husks or rice hulls and the biogenetic silica takes the form of ash.

The invention will now be explained and described in detail with reference to the drawings, in which:-

20 Fig. 1 is a schematic diagram of a furnace for conducting tests for the production of rice husk ash;

Fig. 2 is a graph showing the grading curve for ground rice husks;

Figs. 3-7 are graphs showing the temperature-time 25 relationships for tests on rice husks using the furnace shown in Fig. 1; and Fig. 8 is a diagrammatic representation of a furnace suitable for the continuous production of rice husk ash by the method according to the invention.

Tests have been carried out on rice husks using the tube

furnace 1 shown in Fig. 1 of the drawings which had a
heated length of 700mm and a tube of 75mm inner
diameter. A ceramic lining tube 2 of 60mm inner
diameter was then set up within the furnace and was
supported by a friction drive arrangement (not shown) to
allow rotation. In order to retain material in the
central section (approx. 300mm) of the tube during
combustion, two loosely fitting discs 3, 5 were inserted
on the ends of respective tubes 4, 6. Air was passed
through the tube 4 as indicated by the arrow and a
thermocouple 7 was inserted in the other tube 6.

Rice husks were obtained from Tarragona and tests were carried out on ground and unground husk. The grading of the ground husks is shown in Figure 2 of the drawings. The bulk densities of the ground and unground husks were 513 and 107 kg/m³ respectively. Two temperatures and two different combustion times were chosen and in all five tests were conducted as follows:-

			Target temp. I		ime	
		Ground husk	450 <sup>O</sup> C	30	min	
	Test 1	Ground husk	750 <sup>0</sup> C	60	min	
25	Test 2		450 <sup>O</sup> C	60	min	
	Test 3	Ground husk	750 <sup>0</sup> C	30	min	
	Test 4	Ground husk	450 <sup>O</sup> C	60	min	
	Test 5	Unground husk	450 6			

)

The upper target temperature was limited to 750°C in order to ensure that no overshoot above the acceptable limit could occur.

PCT/GB94/02106 WO 95/10488

**-** 5 **-**

The tube was first charged with the husk and the tube allowed to rotate for a short period in order to distribute the material uniformly. A speed of rotation of 1 rpm was adopted. The furnace was then set to the target temperature. Both the temperature in the furnace windings and the inner tube were monitored and minor adjustments made as necessary during the course of the tests.

In order to ensure a free tumbling effect, the tube was filled to a depth of no more than about one-third of its diameter. For the ground husk roughly 90g was introduced. In the case of the unground husk it was necessary to place a greater than ideal bulk in order to ensure a reasonable return; 42g was introduced in this case.

1

After maintaining the furnace at the set temperature for the required period it was allowed to cool. For the tests conducted at 450°C it was possible to withdraw the inner tube immediately and allow it to cool protected against excessive cooling rates, which might have damaged it, by an insulating blanket or a foil shield. At the higher temperature it was not possible to remove the inner tube and it had to be left overnight to cool.

The ash was then raked from the tube and material which was retained in the central section throughout the combustion was separated from that which had been transported further along the tube.

Although the temperature rise of the furnace was quite rapid, it has to be accepted that the ash was held at a high temperature for an additional period whilst cooling

was allowed. This was not a serious problem at the lower temperature, but must clearly be allowed for in interpreting the findings from the high temperature tests.

- Figures 3-7 show the temperature-time relationships for the tests and the main events occurring during the tests are indicated on these graphs together with the 30 or 60 minute hold period. The furnace temperature and the temperature in the lining tube are shown.
- 10 The furnace temperature was controlled by a thermocouple in the furnace windings and clearly the temperature in the inner tube would be lower than this until equilibrium had been reached, with the possible exception of the temperature being raised temporarily due to the combustion itself. The furnace was initially set for a temperature 50°C above the target and minor adjustments made in the later stages as necessary.

It was found that the temperature recorded by the thermocouple in the lining tube was lowered by about 70°C by the passage of air through the tube and this must be allowed for when interpreting the results.

)

For handling reasons it was necessary to introduce the husk into the furnace cold and then raise the furnace temperature. As can be seen from the graphs, this occurred fairly rapidly, reaching 500°C within 15 minutes. Early in the heating, water vapour was driven off and smoke emission commenced when the temperature in the lining tube reached 180°C. At this stage the air

1

)

supply was turned on. During the combustion phase there was a rapid rise in temperature in the lining tube, briefly overtaking the furnace temperature in tests 3, 4 and 5. Combustion was completed within 10-20 minutes, which, in some cases, was before the target temperature was reached.

With the ground husk, some fine, partly burned particles were carried out with the air flow, but the unground husk was retained within the tube.

- 10 After burning for the required time, the ash was removed from the tube taking care to separate material which had been transported out of the central section during combustion and using only the material which had been retained in the central section for subsequent analysis.
- 15 The analysis of the ash samples was in three parts:
  - (a) Determination of carbon, hydrogen and nitrogen content,
  - (b) EDAX analysis to determine the amounts of silicon and metallic elements present,
- 20 (c) X-ray diffraction analysis to establish the forms of silica present.

The results of these analyses were as follows, with contents expressed as percentages by weight:

Element	1C	2C	3C	4C	5C
С	2.10	1.48	2.14	1.35	2.10
Н	0.19	-	0.93	0.10	0.19
N	-	-	-	-	-
Si	87.48	86.01	86.47	84.84	93.46
K	4.98	4.92	6.27	5.97	1.26
Fe	0.87	0.35	0.63	0.86	0.01
Cu	4.49	4.33	2.94	3.72	2.37
Zn	2.18	2.35	2.59	1.99	1.60
Ca	· -	2.04	1.11	2.62	1.30

The X-rd report on silicon dioxide crystallinity found the following:

- Sample 1C Almost completely amorphous; small amount (fraction of a percent) of unidentified material, possible a feldspar.
  - Sample 2C Approximately 1% cristabolite; traces of unidentified material (as 1C) and possibly quartz.
  - Sample 3C As 1C.
- 20 Sample 4C As 2C.
  - Sample 5C Completely amorphous.

**-** 9 **-**

It is thought that the traces of unidentified material relates to contamination from a previous use of the grinder. This would be consistent with its possible identification as a feldspar. The same is true of the higher potassium and, to a lesser extent, copper contents of the ground husk ash samples. The grinder had previously been used for clay and soil samples and there is the possibility that contamination occurred.

All samples of ash produced satisfy the requirement of a high amorphous silica content. Hence the principle that a usable ash can be produced at low temperatures and in a short time is established on a small scale. The retention time in the furnace after combustion had no advantageous effect on the end product and could probably be reduced further.

)

)

The key factor is to ensure that husks or husk particles are kept separated from each other as far as possible during the combustion, achieved here by the use of a rotating tube furnace with a small charge of material.

20 If too much material is introduced there is a risk that the temperature will rise excessively due to the exotherm during combustion. This is clearly indicated in Test 5, in which a greater volume of material was used and there was a very sharp rise in temperature during combustion. If the temperature reached becomes too high then the crystalline content of the ash will increase.

Pre-grinding of the husk before burning does not appear to offer any advantage in the light of the short 30 combustion time involved. In terms of final ash composition, the unground husk gave the best result.

There are, however, other advantages to be gained from grinding beforehand arising from the increase in the bulk density, namely reduction in transportation costs and permitting a greater furnace throughput. The ground particle size used in these tests was probably smaller than the optimum as some particles were small enough to be transported through the furnace in the airflow despite the fact that this was kept at the lowest possible level.

10 The tests indicated that rice husk ash could be produced in a relatively short time if the furnace was maintained at 450°C under the right conditions and thus made the ash production on a commercial basis an economic possibility. If the rice husks can be moved through a furnace on a continuous basis and agitated while they are heated, heating times can be reduced to 15 to 20 minutes.

)

)

Accordingly, the furnace shown diagrammatically in Fig. 8 of the drawings is employed. As shown in Fig. 8, the 20 furnace comprises an inclined tube 11 which is mounted on support stands (not shown) for rotation about its longitudinal axis by suitable drive means (likewise not The furnace is provided substantially throughout its length with heating elements (also not 25 shown). The furnace is further provided, at or adjacent to its upper end, with a hopper 12 through which rice husks, which may be ground, are fed to the furnace by means of a screw feeder 13. A smoke outlet 14 leads from the tube furnace 11 to a filter 15 which is mounted in a rotating holder 16 and the filtered air is led from the filter 15 to an air extraction system (not shown) via a pipe 17. The end of the furnace tube 11 remote from the feed hopper 12 is provided with an ash

- 11 -

collection can 18 at which the ash is collected. The hopper 12, furnace tube 11 and ash collection can 18 are mounted on a platform 19 which can be tilted by means of an adjusting jack 20 to ensure that the hopper 12 is located at a level which is higher than that of the can 18 so that material fed to the furnace tube 11 will tend to pass down the tube from the hopper 12 to the can 18. The platform 19 is further desirably provided with wheels 21 whereby the apparatus is portable and the adjusting jack 20 is desirably also provided with similar but smaller wheels 22.

1

)

The furnace is desirably rotated at a speed of about 1 rpm and is set at a temperature of  $450^{\circ}$ C. The retention time of the rice husks in the furnace is determined by the rate of rotation of the tube 11 and the angle of declination of said tube. However, under ideal conditions it should be possible to collect ash from the can 18 some fifteen minutes after the rice husks enter the furnace from the hopper 12. Thus a continuous production of rice husk ash on a commercially economic basis is assured.

The ash has a high amorphous silica content and can be used for the production of dense concrete and aircrete blocks. Because of the good combustion conditions, the ash also has a low carbon content (approximately 2% by weight) which is a highly desirable feature because a higher level of carbon reduces ash reactivity.

Although the invention has been described above with reference to the production of ash from rice husks it should be noted that the invention is not restricted to the production of rice husk ash but is applicable generally to the production of biogenetic silica from organic plant matter.

- 12 -

#### CLAIMS

- A method for the production of biogenetic silica from organic plant matter in which the plant matter is fed continuously to an inclined rotary furnace maintained at a temperature of between 400 and 500°C, the material is retained in the furnace for no more than about 30 minutes and biogenetic silica is continuously collected from the furnace and allowed to cool.
  - 2. A method according to claim 1, wherein the rotary furnace is maintained at a temperature of about 450°C.

)

)

- 3. A method according to claim 1 or claim 2, wherein the material is retained in the furnace for between 15 and 30 minutes.
- 4. A method according to any preceding claim, wherein the organic plant material is fed into the upper end of the inclined rotary furnace via a hopper.
- 5. A method according to any preceding claim, wherein the biogenetic silica is collected from the lower end of the inclined rotary furnace via a chute.
- 6. A method according to any preceding claim, wherein the organic plant matter is ground to a powder before being fed to the furnace.
- 7. A method according to any preceding claim, wherein the organic plant matter takes the form of rice husks or rice hulls and the biogenetic silica takes the form of ash.

1

)


- 8. Apparatus for performing the method claimed in any one of the preceding claims, said apparatus including a furnace which comprises an inclined tube (11) mounted on support stands for rotation about its longitudinal axis, means for rotating the inclined tube about its said longitudinal axis and a plurality of heating elements located in the furnace substantially throughout the length of the tube; a hopper (12) for receiving organic plant matter; means for feeding the organic plant matter from the hopper to the furnace at one end of the tube and means for collecting combusted material from the other end of the tube.
  - 9. Apparatus according to claim 8, wherein the means for feeding organic plant matter from the hopper (12) to the tube (11) comprise a screw conveyor (13).
  - 10. Apparatus according to claim 8 or claim 9, wherein the means for collecting combusted material comprise a collection can (18).
  - 11. Apparatus according to any one of claims 8 to 10, wherein the furnace is provided with a smoke outlet (14) which leads to a filter (15) mounted in a rotating holder (16) and leading to an air extraction system.
  - 12. Apparatus according to any one of claims 8 to 11, wherein the furnace is mounted on a platform (19) having means for adjusting the angle of inclination of the platform and hence of the tube.
  - 13. Apparatus according to claim 12, wherein the adjusting means comprise an adjusting jack (20).


PCT/GB94/02106

- 14. Apparatus according to claim 12 or claim 13, wherein the platform is provided with wheels (21) whereby the apparatus is portable.
- 15. Apparatus according to any one of claims 8 to 14, wherein the means for rotating the tube are arranged to rotate the tube at about 1 rpm.

1/4

FIG. 1







)


1


)

)










. .

)

1

Ì

4/4



21

### INTERNATIONAL SEARCH REPORT

Intern. .al Application No PCT/GB 94/02106

imum doc C 6	SEARCHED currentation searched (classification system followed by classification CO4B F23G	tion symbols)	
umentabo	C04B F23G	,	
	on searched other than minimum documentation to the extent that	such documents are included in the fields so	earched
		described search terms used)	
tronic da	ata base consulted during the international search (name of data ba	ase and, where practical, search with any	
осим	IENTS CONSIDERED TO BE RELEVANT	relevant nassages	Relevant to claim No.
egory °	Citation of document, with indication, where appropriate, of the	Tuevani pa-spir	
	CHEMICAL ABSTRACTS, vol. 113, no	o. 4 <b>,</b>	1,2,7-11
	23 July 1990, Columbus, Ohio, Us	S;	
	abstract no. 28326m, A.F.GALAL ET AL. Rice husk ash		
	portland blended cement		
	see abstract		
	& SILIC. IND.,		
	vol.55, no.1-2, 1990 page 55-8		
	US,A,4 037 543 (J.F.ANGELO) 26	July 1977	1,2,7-11
	see column 7, line 4 - line 24;	claims	
	US,A,4 049 464 (A.TUTSEK ET AL.	) 20	1,7
	Sentember 19//		
	see column 3. line 35 - column	_4, line 5	
	see column 5. line 46 - line 65	<b>5</b>	
	see column 7, line 49 - line 50	<b>D</b>	
		-/	
χFι	urther documents are listed in the continuation of box C.	Y Patent family members are lis	ted in annex.
	categories of cited documents:	T later document published after the	international filing date
'A' doe	rement defining the general state of the art which is not	or priority date and not in confidence of the understand the principle	
COR	usidered to be of particular relevance lier document but published on or after the international	invention	the claimed invention
filis	ng dale	involve an inventive step when the	e document is taken alone
***	nument which may throw doubts on priority claim(s) or sich is cited to establish the public accordance of another	"Y" document of particular relevance	the claimed invention
cit	ation or other special reason (as specified) curnent referring to an oral disclosure, use, exhibition or	document is combined with one ments, such combination being o	
oth	ner means current published prior to the international filing date but	in the art.	
lat	ter than the priority date claimed	'&' document member of the same p	
Date of	the actual completion of the international search	1 0. 01	. <b>9</b> 5
	23 December 1994		
Name a	and mailing address of the ISA	Authorized officer	
i	European Patent Office, P.B. 5818 Patentaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,	_	•
1		Theodoridou, E	

. 1

## INTERNATIONAL SEARCH REPORT

Intern. .al Application No
PCT/GB 94/02106

	INTERNATIONAL CELEBRATIONAL CE	PCT/GB 94/02106
C(Continua	tion) DOCUMENTS CONSIDERED TO BE RELEVANT	Relevant to claim No.
Category	Citation of document, with indication, where appropriate, of the relevant passages	ice can be a second
A	V.M.MALHOTRA 'Fly Ash, Silica Fume, Slag, and Natural Pozzolans in Concrete; Proceedings 4th International Conference, Istanbul, Turkey, May 1992' May 1992, ACI S.SUGITA et al.: 'Evaluation of Pozzolanic Activity of Rice Husk Ash' Volume I see page 495 - page 512	1-7
A	DE,A,25 59 527 (L.&C. STEINMÜLLER GMBH) 31 March 1977 see claims	1-7
A	US,A,4 730 564 (H.I.ABBOUD) 15 March 1988 see claims; figure 1	8-15
A	US,A,2 127 328 (F.J.EGAN) 16 August 1938 see the whole document	8-14
A	GB,A,969 538 (MOUNT ROYAL RICE MILLS LTD) 9 September 1964	1,2,7
1		

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

# INTERNATIONAL SEARCH REPORT Information on patent family members

al Application No PCT/GB 94/02106

Publication date	Patent family member(s)	Publication date
26-07-77	NONE	
20-09-77	DE-A- 2416291 FR-A,B 2266672 GB-A- 1508825 JP-C- 1088485 JP-A- 50140390 JP-B- 56031280 SE-B- 394880 SE-A- 750364	2 31-10-75 5 26-04-78 5 23-03-82 6 11-11-75 6 20-07-81 6 18-07-77
31-03-77	NONE	
15-03-88	NONE	
	NONE	
	NONE	
	26-07-77 20-09-77 31-03-77	20-09-77 NONE  20-09-77 DE-A- 2416293 FR-A,B 2266673 GB-A- 1508825 JP-C- 1088485 JP-A- 50140390 JP-B- 56031280 SE-B- 39488 SE-A- 750364  31-03-77 NONE  15-03-88 NONE  NONE

# This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

## BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:
Defects in the images include out as
☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
☐ FADED TEXT OR DRAWING
☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
COLOR OR BLACK AND WHITE PHOTOGRAPHS
GRAY SCALE DOCUMENTS
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
OTHER:

# IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.